

## DS 28 750 PP TOP SK

Gramatura	EN 1849-2	700 g/m <sup>2</sup>
Debelina		0,9 mm
Vrednost Sd		95 m
Lepilo TOP SK		bitumenski
Odpornost na pretrg MD/CD*	EN 12311-1	530 / 350 N/50mm
Trganje ob vijaku MD/CD*	EN 12310-1	200 / 200 N
Artikel TOP SK		02064019



## DS 48 1000 PP

Gramatura	EN 1849-2	1000 g/m <sup>2</sup>
Debelina		1,0 mm
Vrednost Sd		106 m
Lepilo TOP SK		-
Odpornost na pretrg MD/CD*	EN 12311-1	470 / 360 N/50mm
Trganje ob vijaku MD/CD*	EN 12310-1	195 / 220 N
Artikel		02064014



## DS 48 1100 PP / DS 48 1100 PP TOP SK

Gramatura	EN 1849-2	1100 g/m <sup>2</sup>
Debelina		1,1 mm
Vrednost Sd		152 m
Lepilo TOP SK		akrilni
Odpornost na pretrg MD/CD*	EN 12311-1	700 / 440 N/50mm
Trganje ob vijaku MD/CD*	EN 12310-1	220 / 230 N
Artikel / Artikel TOP SK		02064005 / 02064020



## DS 48 1300 TOP SK

Gramatura	EN 1849-2	1300 g/m <sup>2</sup>
Debelina		1,3 mm
Vrednost Sd		152 m
Lepilo TOP SK		akrilni
Odpornost na pretrg MD/CD*	EN 12311-1	730 / 450 N/50mm
Trganje ob vijaku MD/CD*	EN 12310-1	250 / 250 N
Artikel TOP SK		02064013



## DS 48 2200 TOP SK

Gramatura	EN 1849-2	2200 g/m <sup>2</sup>
Debelina		2,0 mm
Vrednost Sd		150 m
Lepilo TOP SK		bitumenski
Odpornost na pretrg MD/CD*	EN 12311-1	500 / 400 N/50mm
Trganje ob vijaku MD/CD*	EN 12310-1	130 / 130 N
Artikel TOP SK		02064021



\*MD = po dolžini CD = po širini

Riwega srl ne nosi odgovornosti za nepravilno rabo njenih proizvodov